


Boost[®] Hybrid Roof

REFLECTIVE INSULATING
BREATHER MEMBRANE

ROOFS



USE ON THE
COLD SIDE OF
THE BUILDING
FABRIC IN ROOFS





COMPLIES WITH
EN 13859-1 AND
EN 13859-2

ACTIS

TOMORROW'S INSULATION TODAY

Boost[®] Hybrid Roof is a multifoil insulation product with a built-in breather membrane function and an exceptional thermal performance.

Boost[®] Hybrid Roof provides dual properties within a single product: a breathable membrane and insulation, allowing a reduction in the number of installation steps whilst reducing the thickness of the main insulation to achieve the same required U-Value. It can be used in conjunction with any type of insulation.



PROPERTY

Area : 15 m²
 Width : 1.5 m
 Length : 10 m
 Weight/m² : 650 g / m² (+/- 5%)
 Thickness : 35 mm (+/- 5 mm)

R=2.15*
 m².K/W

* EN 16012 with 2 air voids and horizontal heat flow

PRODUCT

DECLARED THERMAL PERFORMANCE (INNER/OUTER SIDE)		
R Value + 2 air cavities after ageing	Horizontal Heat Flow 2.15m ² .K/W	EN 16012
Core R-Value	1.35 m ² .K/W	
Declared Emissivity after ageing	0.05 / 0.9	
TENSILE STRENGTH		
Longitudinal direction	> 300 N / 50 mm	EN 12311-1 & EN 13859-1/2 Annex A
Transversal direction	> 150 N / 50 mm	
Elongation (Longitudinal)	> 15%	
Elongation (Transversal)	> 10%	
RESISTANCE TO TEARING, NAIL SHANK		
Longitudinal direction	> 150 N	EN 12310-1 & EN13859-1/2 Annex B
Transversal direction	> 150 N	
WATER VAPOUR TRANSMISSION		
Vapour Resistance (Z)	0.55 MNs/g	EN 12572 set C
Vapour Resistance of external layer	0.25 MNs/g	
Diffusion eq.air layer thickness (Sd)	≤ 0.11m	
WATERTIGHTNESS		
	Watertight, W1	EN 1928 Method A
AIR PERMEABILITY		
	< 0.030 m ³ / (m ² x h x 50 Pa)	EN 12114
FLEXIBILITY AT LOW TEMP		
	-30/30 °C / ø30mm	EN 1109
DIMENSIONAL STABILITY		
	+80°C/6H ← 1%	EN 1107
REACTION TO FIRE		
	NPD (No Performance Determined)	
WIND UPLIFT RESISTANCE		
	Suitable for all wind zones (1-5) throughout the UK	BS5534

ACTIS

TOMORROW'S INSULATION TODAY

ACTIS - Tel : +44 (0) 1249 462888
 Email : solutions@insulation-actis.com

www.insulation-actis.com

